

**TEST REPORT ISSUED BY LGAI TECHNOLOGICAL CENTER, S.A.****CLIENT IDENTIFICATION INFORMATION**

**NAME:** TECNOPOL SISTEMAS, S.L  
**CENTRE:** TECNOPOL SISTEMAS, S.L  
**ADDRESS:** PRENSA, 5

**CITY:** PARETS DEL VALLES  
**PROVINCE:** 08150 BARCELONA  
**COUNTRY:** SPAIN

**SAMPLE IDENTIFICATION INFORMATION:**

**PRODUCT:** P-2049-1 (100% PURE POLYUREA)  
**SUPPLIER:**  
**BRAND:**  
**BATCH:**  
**CATEGORY:**  
**REMARKS:** Submitted by the client.

**SHIPMENT DATE:**  
**EXP. DATE:**  
**T. M. PRODUCT Tº:**  
**Y/ REF:**

**SAMPLE TAKING DATE:**  
**RECEPTION DATE:** 09/12/09  
**BAR CODE:**  
**SECTION:**

**CHEMICAL AND PHYSICAL TESTING LAB**

Start 09/12/09 End 25/01/10

**Characteristics of the materials**

	Parameter	Result	Legislative Rule
1	Migration of materials in contact with drinking water	Performed	

**Product Characteristics**

	Parameter	Result	Legislative Rule
2	Reaction at 20 ppm chlorine	No changes	No anomalous change
3	Conductivity (µS/cm)	<20.0	<=2500
4	Colour (mg/Pt/Co)	<1.0	<=15
5	Odour: Dilution rate	1	<=3
6	Flavour: Dilution rate	1	<=3

**Content control**

	Parameter	Result	Legislative Rule
7	Turbidity (UNF)	0.48	<=5
8	Ammonia (mg/l)	<0.5	<=0.5
9	Total Organic Carbon (TOC) (mg/l)	13.0	No changes
1	Cyanides (CN) (µg/l)	<5.0	<=50
1	Combined residual chlorine (mg/l)	<0.5	<=2
1	Residual free chlorine (mg/l)	<0.5	<=1
1	pH (upH)	6.5	>=6.5 <=9.5
1	Nitrites (mg/l)	<0.5	<=0.5
1	Oxidizability (mg O2/l)	1.7	<=5
1	Sodium (Na) (mg/l)	1.7	<=200
1	Chlorides (mg/l)	3.3	<=250

English translation of de original in Spanish

This document may only be reproduced in full.

The results obtained refer only to the tested sample.

Registered at the Business Register of Barcelona, Volume 35803, Folio 1, Page Nº 266.627, 1st Recording. Tax Identification Nº: A-63.207.492.

**TEST REPORT ISSUED BY LGAI TECHNOLOGICAL CENTER, S.A.****CHEMICAL AND PHYSICAL TESTING LAB**

Start 09/12/09 End 25/01/10

1	Fluorides (F)	(mg/l)	<0.1	<=1.5
1	Nitrates	(mg/l)	<0.5	<=50
2	Sulphates	(mg/l)	<1.0	<=250
2	Aluminium (Al)			<=200
	First migration	(µg/l)	3.0	
2	Antimony (Sb)	(µg/l)	<2.0	<=5
2	Arsenic (As)	(µg/l)	<2.0	<=10
2	Boron (B)	(mg/l)	<0.1	<=1
2	Cadmium (Cd)	(µg/l)	<1.0	<=5
2	Copper (Cu)	(mg/l)	<0.2	<=2
2	Chromium (Cr)	(mg/l)	<2.0	<=50
2	Iron (Fe)	(µg/l)	<10.0	<=200
2	Manganese (Mn)	(µg/l)	<2.0	<=50
3	Mercury (Hg)	(µg/l)	<0.2	<=1
3	Nickel (Ni)	(µg/l)	<2.0	<=20
3	Lead (Pb)	(µg/l)	<2.0	<=25
3	Selenium (Se)	(µg/l)	<2.0	<=10
3	Volatile organic compounds			
	1,2 Dichloroethane	(µg/l)	<0.5	<=3
	Trichloroethane + Tetrachloroethane	(µg/l)	<1.0	<=10
3	Trihalomethanes	(µg/l)	2.9	<=100
3	Benzene	(µg/l)	<0.5	<=1
3	Polycyclic Aromatic Hydrocarbons			
	Benzopyrene	(µg/l)	<0.01	<=0.01
	Sum of Polycyclic Aromatic Hydrocarbons	(µg/l)	<0.01	<=0.1
3	Pesticides			
	Aldrin	(µg/l)	<0.01	<=0.03
	Dieldrin	(µg/l)	<0.01	<=0.03
	Heptachlorine	(µg/l)	<0.01	<=0.03
	Heptachlorine epoxide	(µg/l)	<0.01	<=0.03
	Individual pesticide	(µg/l)	<0.01	
	Total pesticides	(µg/l)	<0.50	<=0.5
3	Acrylamide			<=0.1
	First migration	(µg/l)	<0.1	<=0.1
4	Epichloridrine	(µg/l)	<1.0	<0.1

LGAI TECHNOLOGICAL CENTER, S.A.  
Campus UAB  
C/ta. de Acceso a la Universidad de Medicina, s/n  
08193 Bellaterra (Barcelona)  
Tlf.: 93 5672000 Fax: 93 5672001

**TEST REPORT ISSUED BY LGAI TECHNOLOGICAL CENTER, S.A.****CHEMISTRY DEPARTMENT**

Note: N. D. = Not Detected. The detection limit for the technique used is 1µg/l

According to Annex I of Royal Decree 140/2003, the maximum limit set for Epichlorohydrin is 0.1µg/l. Mass Gas Chromatography is the technique used to determine this parameter. Even with the best possible optimization, this technique does not enable reaching a detection limit lower than 1 µg/l.

The parameter determination, except for the migration at the reaction at 20 ppm of chlorine, has been carried out at a collaborating Laboratory, under record number 702790.

Migration for polymeric materials:

-Extraction means: Chlorinated water containing 1 ppm chlorine.

-Migration Temperature: 40°C.

-Contact time: The sample is washed several times, as instructed in Standard EN-12873.

Next, three 72-hour cycles are performed, thereby obtaining three testing samples.

Parameters are analysed during the initial 72-hour cycle; only the parameters that are beyond the limits of RD 140/2003 in the first cycle are repeated in the second and third cycle.

-Volume of the sample: 1 litre for each of the 72-hour cycles.

-Contact surface: 500 cm<sup>2</sup>.

-Surface/volume ratio: 500 cm<sup>2</sup>/l.

**CONCLUSION**

Regarding the analysed parameters, the material complies with the requirements established in Royal Decree 140/2003. Although no epichlorohydrin has been detected, it should be mentioned that its detection limit is higher than the one stated, since the technique used does not allow reaching a detection limit lower than 1 µg/l.

**METHODOLOGY USED**

Q 1 EN 12873	Q 2 Internal method
Q 3 Internal method	Q 4 Internal method
Q 5 Internal method	Q 6 Internal method
Q 7 Internal method	Q 8 Internal method
Q 9 Internal method	Q 1 Internal method
Q 1 Internal method	Q 1 Internal method
Q 1 Internal method	Q 1 Internal method
Q 1 Internal method	Q 1 Internal method
Q 1 Internal method	Q 1 Internal method
Q 1 Internal method	Q 2 Internal method
Q 2 Internal method	Q 2 Internal method
Q 2 Internal method	Q 2 Internal method
Q 2 Internal method	Q 2 Internal method
Q 2 Internal method	Q 2 Internal method
Q 2 Internal method	Q 3 Internal method
Q 3 Internal method	Q 3 Internal method
Q 3 Internal method	Q 3 Internal method
Q 3 Internal method	Q 3 Internal method
Q 3 Internal method	Q 4 Internal method



LGAI TECHNOLOGICAL CENTER, S.A.  
Campus UAB  
C/ta. de Acceso a la Universidad de Medicina, s/n  
08193 Bellaterra (Barcelona)  
Tlf.: 93 5672000 Fax: 93 5672001

**TEST REPORT ISSUED BY LGAI TECHNOLOGICAL CENTER, S.A.**

LGAI Technological Center, S.A.

Isabel Garmendia Arnau  
Chief of the Inorganic Chemistry Department  
LGAI Technological Centes S.A.

**English translation of de original in Spanish**

**Service Quality Guarantee**

Applus+, guarantees that this task has been carried out in compliance with the requirements of our Quality and Sustainability System, and furthermore, that the contractual terms and legal regulations have been complied with.  
In the framework of our improvement programme, we would appreciate any comments you may deem appropriate. These should be addressed to the manager who signs this document, or to the Quality Director of Applus+ at the following address: satisfaccion.cliente@appluscorp.com